

ORGANIC FLAME TREATMENT

FST006

PROPERTIES

None hygroscopique solution
 Water white

Excellent for any type of wood exotic woods, rosewood, ebony, american walnut, etc...

TECHNICAL DATA

1) Color:	Clear	Sand with 220 grit
2) Appearance:	Non color liquid	Apply 1 coat at 2 to 3 mils wet to the whole complete surface
3) Weight/gallon:	9.62 lbs / US Gal. 11.59 lbs / Imperial	Air dry 12 hour
4) VOC	0 lbs / US Gal. 0 lbs / Imperial Gal.	Or
Comply with	FAR 25.853 A & B	30 minutes @ 120°F

METHOD OF APPLICATION

Conventional:	Spray gun HVLP Fluid tip fine finish	Air assisted airless	Air pressure 45-50 P.S.I.G. Air flow 30-35 S.C.F.M.
----------------------	---	-----------------------------	--

For more information, please contact our Technical Support Department at Duro-Lak inc Phone : (450) 687-4140

NOTE: The information, rating & opinion stated above pertain to a material currently offered and represent the result of laboratory evaluation. The customer's application and other requirements are unknown, or are not under our control, the company cannot make any warranties or guarantees as to results.

DISCLAIMER: Neither Duro-Lak Inc. nor its marketing agents shall be responsible for the use of this information, or of any product, method or apparatus mentioned. You must have your own determination of product suitability and thoroughly qualify it for serviceability, for environmental acceptability, and for impact on the health and safety of your employees and purchases of your products. Duro-Lak's only obligation shall be to replace such quantity of the product which is proven to have been defective. No person is authorized to make any statement or recommendation not contained herein, and any such